Chain - Guide Profiles


REXNORD

· Material: Polyethylene UHMWPE with molecular density 5.600.000 g/mol. Characteristics: new material Polyethylene ULF™


brown red (UHMWPE): reduced friction coefficient, higher wear resistance.

- Linear expansion coefficient: 2 x 10⁻⁴ °C⁻¹ Calculation of thermal expansion see Technical information.
- Operating temperature Green Black: In air (- 40 to + 80 °C). In hot water (+ 70 °C).
- Operating temperature ULF[™] brown red: In air (- 40 to + 45 °C). In hot water (+ 45 °C).
- Polyethylene ULF™ is FDA approved Polyethylene ULF™ complies with the Code of Federal Regulations Title 21, § 177.1520 "Olefin Polymers" of the Food and Drug Administration (FDA) of April 1, 2008.
- Coefficient of friction between chain POM and wearstrip ULF™: 0,08. Note: for calculation of chain pull refer to Technical Support.
- Position of guides. See Technical information.


📒 Chain - guide profile



Part. **S0884**




- Packaging: 24 metres.



- Can be used in combination with Part. S0884 - S0368.

Chain - guide profile

Part. S0886



- Can be used in combination with Part. S0884 - S0368.







Item code for order = Part. + Code