## **Chain - Guide Profiles**


REXNORD

 Material: Polyethylene UHMWPE with molecular density 5.600.000 g/mol.
Characteristics: new material Polyethylene ULF™

brown red (UHMWPE): reduced friction coefficient, higher wear resistance.

- Linear expansion coefficient: 2 x 10<sup>-4</sup> °C<sup>-1</sup> Calculation of thermal expansion see Technical information.
- Operating temperature Green Black: In air (- 40 to + 80 °C). In hot water (+ 70 °C).
- Operating temperature ULF<sup>™</sup> brown red: In air (- 40 to + 45 °C). In hot water (+ 45 °C).
- Polyethylene ULF<sup>™</sup> is FDA approved Polyethylene ULF<sup>™</sup> complies with the Code of Federal Regulations Title 21, § 177.1520 "Olefin Polymers" of the Food and Drug Administration (FDA) of April 1, 2008.
- Coefficient of friction between chain POM and wearstrip ULF™: 0,08. Note: for calculation of chain pull refer to Technical Support.
- Position of guides. See Technical information.

📒 Chain - guide profile




Metal profile material	Length metres	Code	Weight kg/m
Austenitic stainless steel	3	64066	- - 0,90 -
	6	69645	
Ferritic stainless steel	3	693292	
	6	693302	

- Use: recommended with MatTop® chains in abrasive environment / high speed / high temperature.


- Packaging: 18 metres.

📒 Chain - guide profile

## Part. **S0885**



- Can be used in combination with Part. S0368 - S0884.



- Can be used in combination with Part. S0368 - S0884.



Part. **S0368** 

Item code for order = Part. + Code